

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09D 151/00, C08F 283/01, 290/14		A1	(11) International Publication Number: WO 99/51696
			(43) International Publication Date: 14 October 1999 (14.10.99)
<p>(21) International Application Number: PCT/EP99/02279</p> <p>(22) International Filing Date: 30 March 1999 (30.03.99)</p> <p>(30) Priority Data: GB 9807213.5 4 April 1998 (04.04.98) GB</p> <p>(71) Applicant (for all designated States except US): IMPERIAL CHEMICAL INDUSTRIES PLC [GB/GB]; Imperial Chemical House, Millbank, London SW1P 3JF (GB).</p> <p>(72) Inventors; and</p> <p>(75) Inventors/Applicants (for US only): BODE, Daniel [US/US]; 2157 West 38th Street, Cleveland, OH 44113 (US). HOWARD, Deborah [GB/GB]; 78 Sycamore Road, Kingsbury, Tamworth B78 2JL (GB). BRADLEY, Christopher [GB/GB]; 141 Barrows Lane, Yardley, Birmingham B25 1SE (GB). BELTON, Martin [GB/GB]; 10 Hole Farm Way, Hawkesley, Birmingham B38 9RW (GB).</p> <p>(74) Agent: WARD, Steven, Paul; Patents & Trade Marks Section, Legal Affairs Department, ICI Paints, Wexham Road, Slough, Berkshire SL2 5DS (GB).</p>		<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published With international search report.</p>	
(54) Title: AQUEOUS COATING COMPOSITION			
(57) Abstract			
<p>A protective coating composition for coating interior surfaces of beer, beverage, and food containers, as well as interior and exterior surfaces of can ends, comprises a polymeric binder of emulsion copolymerised ethylenic monomers in the presence of an unsaturated polyester dispersed into water with an aqueous dispersed epoxy-acrylic graft copolymer dispersant. The preferred polymeric binder comprises by weight between 0.1 % and 40 % unsaturated polyester, between 20 % and 80 % emulsion copolymerised ethylenic unsaturated monomers, and at least 20 % dispersant, where the emulsion copolymerised monomers cross-link with the water dispersed unsaturated polyester.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

AQUEOUS COATING COMPOSITION

This invention relates to aqueous coating compositions particularly useful as can coatings for beverage and food containers, a process for making the
5 compositions and a process for using them.

Industrial coatings are surface protective coatings (paint coatings) applied to substrates and typically cured or crosslinked to form continuous films for decorative purposes as well as to protect the substrate. A protective coating ordinarily comprises an organic polymeric binder, pigments, and various paint
10 additives, where the polymeric binder acts as a fluid vehicle for the pigments and imparts rheological properties to the fluid paint coating. Upon curing or crosslinking, the polymeric binder hardens and functions as a binder for the pigments and provides adhesion of the dried paint film to the substrate. The pigments may be organic or inorganic and functionally contribute to opacity and
15 colour in addition to durability and hardness. Protective coatings which contain little or no opacifying pigments are described as clear coatings. The manufacture of protective coatings involves the preparation of a polymeric binder, mixing of component materials, grinding of pigments in the polymeric binder, and thinning to commercial standards.

Epoxy resins are particularly desirable for use in protective surface coatings materials as a vehicle or polymeric binder for the pigments, fillers, and other additives where the epoxy resins advantageously provide toughness, flexibility, adhesion, and chemical resistance. Water-dispersed coating compositions
5 containing epoxy resins are highly desirable for can coating compositions and are particularly useful for interior surfaces of containers. Coatings for the interior of soft drink and beer cans, for instance, are critical due to taste sensitivity wherein such can coatings must not alter the product taste of beverages in the containers. Taste problems can occur in a variety of ways such as by leaching of coating
10 components into the beverage, or by absorption of flavour by the coating, or sometimes by chemical reaction, or by perhaps some combination. The closure ends of cans are typically produced by stamping circular end caps from pre-coated flat metal where the top end ordinarily contains a stamped opening profile adapted to snap and roll back to provide an opening. The coating for ends must be resilient
15 and avoid stringing while maintaining good interior resistance to the food or beverage contents.

Container coating technology frequently utilises an epoxy resin which has been grafted with acrylic monomers, styrene, and methacrylic acid. This grafted epoxy resin is prepared in solvent, usually butyl cellosolve and/or n-butanol, to
20 maintain low processing viscosities and then reduced with water by a direct or inverse let down procedure. Although cured film properties are highly desirable, such coatings suffer from the fact that sizeable amounts of solvents are required to obtain good performance. High molecular weight epoxy resins typically require 25% to 50% solvent (based on total solids plus organic solvent) before reducing
25 with amine and water. Also, epoxy coatings used for beverage or food containers raise a concern that such coatings may contain low molecular weight epoxy fragments which could leach out of the coating and into the contents of the container.

Epoxy based can coatings comprising a carbon grafted acrylic chain are
30 disclosed in US Patent No. 4 212 781 which teaches a carbon grafting process

involving solvent polymerisation at moderate temperatures with high levels of peroxide initiator to produce a carbon-graft polymer. The high solvent levels, however, invariably carry over to the aqueous dispersion when the resulting polymers are dispersed into water to produce a VOC (volatile organic compounds) level considerably above 2 and typically between 3 and 4 pounds volatile organic compounds per gallon of resin solids. The acrylic grafted epoxy is particularly useful when utilised with a co-reactive crosslinking melamine crosslinker.

PCT application WO 96/10612 discloses a can coating composition containing both water and organic solvent base on a polymer comprising the reaction of a carboxyl addition polymer and an epoxy resin in the presence of a tertiary amine catalyst. The epoxy and carboxyl addition polymer are pre-formed by co-reacting in organic solvent and subsequently dispersed into water. Similarly, US Patent No. 5 296 525 discloses can coatings based on styrene monomer copolymerised with an epoxy ester copolymer to provide a carboxyl functional polymer for subsequent dispersing into water.

US Patent No. 4 683 273 teaches an epoxy coating composition based on a polymeric blend of an epoxy-acrylic graft copolymer combined with a low molecular weight polyester and an amine crosslinking component. Upon heat curing the coating, the amine crosslinks co-reactive groups on the epoxy-acrylic graft polymer and the low molecular weight polyester.

US Patent No. 5 532 297 pertains to can coatings based on an epoxy-acrylic graft copolymer dispersed into water and subsequently overpolymerised with mono-ethylenically unsaturated monomers and minor amounts of divinyl benzene for crosslinking during the emulsion polymerisation step. Similarly, US 5 464 885 discloses a carboxyl functional epoxy-ester comprising an epoxy esterified with an unsaturated polyester where the epoxy-ester is dispersed into water and subsequently emulsion copolymerised with ethylenically monomers.

It now has been found that high quality can coatings can be produced with little or no organic solvent and without epoxy resin fragments by pre-forming an

unsaturated polyester, dispersing the polyester into water with an epoxy-acrylic graft copolymer dispersant, and then aqueous emulsion copolymerising with ethylenically unsaturated monomers. The resulting aqueous dispersed copolymer provides a highly flexible polymeric coating film with considerable physical and
5 taste resistance to acidic beverages and sterilisation often required for food containers. An emulsion copolymer of polyester with copolymerised acrylic or vinyl monomers produces a coating composition particularly suitable for metal containers capable of being tooled into container end caps. On metal can interior surfaces, the coating provides good flavor resistance and maintains good
10 resistance to sterilisation. The emulsion copolymer of this invention does not require conventional surfactants and avoids blush film problems associated with surfactants used in conventional latex polymerisation processes. These and other advantages of this invention will become more apparent by referring to the details of the invention.

15 According to the present invention there is provided an aqueous dispersed, protective coating composition containing an emulsion copolymer polymeric binder substantially free of volatile organic compounds, the polymeric binder comprising by weight:

(a) between 0.1% and 40% of a preformed, low molecular weight unsaturated
20 polyester having a weight average molecular weight between 1000 and 3000, the unsaturated polyester synthesised by esterifying excess molar equivalents of polyol with lesser molar equivalents of dicarboxylic acid, at molar percents between,

- (i) 0.5 and 50 mol percent polyol consisting of glycol,
- 25 (ii) 10 and 35 mol percent aliphatic dicarboxylic acid,
- (iii) 5 and 35 mol percent aromatic dicarboxylic acid,
- (iv) 5 and 25 mol percent unsaturated dicarboxylic acid,
- (v) 0 and 3 mol percent polyol having three or more hydroxyl groups;

(b) at least 20%, preferably 20% to 80% of in-situ, emulsion copolymerised ethylenic monomers, where the ethylenic monomers comprise at least 20% styrene based on the weight of the ethylenic monomers copolymerised; and

(c) between 20% and 80% carboxyl functional epoxy-acrylic graft copolymer dispersant, the copolymer dispersant having an Acid No. greater than 30, the copolymer dispersant being by weight 5% to 80% epoxy resin and 20% and 95% copolymerised ethylenically unsaturated monomer including carboxylic acid monomer, the graft copolymer dispersant produced by in-situ, non-aqueous polymerisation of the ethylenically unsaturated monomers in the presence of the epoxy resin and at least 3% peroxide initiator based on the weight of said monomers copolymerised, to produce the carboxyl functional, epoxy-acrylic graft copolymer dispersant;

where components (a), (b) and (c) equal 100%, and the polymeric binder is produced by dispersing the copolymer dispersant (c) into water, and the unsaturated polyester (a) and the monomers (b) being dispersed into water with the copolymer dispersant (c), and the monomers (b) emulsion copolymerised in the presence of the unsaturated polyester (a) to coreact with the unsaturated polyester to form the aqueous emulsion copolymer polymeric binder.

Referring first to the unsaturated polyester, useful polyesters in accordance with this invention comprise the esterification products of excess equivalents of glycols, diols, or polyols with lesser equivalents of dicarboxylic acid or anhydrides or polycarboxylic acids, where the polyester polymers are unsaturated polyesters containing ethylenic unsaturation. Linear aliphatic glycols are esterified with lesser equivalents of aromatic dicarboxylic acid and/or linear dicarboxylic acid having between 2 and 36 linear carbon atoms such as adipic, azelaic, succinic, glutaric, pimelic, suberic, or sebacic acid. Unsaturated dicarboxylic acids such as maleic, fumaric or itaconic acid are included to produce unsaturated polyesters. Although not preferred, minor amounts of monocarboxylic unsaturated acid such as acrylic, methacrylic or ethacrylic acid can be esterified. For food

contact coatings, preferred and commercially available linear saturated dicarboxylic acids are dimer fatty acids, or sebacic acid, or cyclohexane dicarboxylic acid, while preferred unsaturated carboxylic acids are maleic and fumaric. Aromatic dicarboxylic acids (anhydrides) include phthalic, isophthalic, 5 terephthalic, and tetrahydrophthalic. Minor amounts of polyfunctional acids such as trimellitic acids can be added if desired. Suitable glycols include linear aliphatic glycols having 2 to 16 carbon atoms such as 1,3- or 1,4-butylene glycol, 2-methyl-1, 3 propanediol, 1,6-hexane diol, neopentyl glycol, propylene glycol, ethylene glycol and diethylene glycol, propylene, and dipropylene glycol, and 10 similar linear glycols. Preferred glycols are diethylene glycol, neopentyl glycol, and 2-methyl-1, 3 propane diol. Although not desirable, minor amounts of polyols can be used such as glycerol, pentaerythritol, dipentaerythritol, or trimethylol ethane or propane. The molar excess of the glycol over the molar amounts of aromatic and linear saturated dicarboxylic acid is between about 2% and 25% and 15 preferably between about 3% and 10%. Preferably between 20 and 50 molar percent of the carboxylic acid components comprises ethylenically unsaturated dicarboxylic acid. The weight average molecular weight of useful unsaturated polyester polymers is preferably between 1500 and 2500.

In accordance with this invention, the polyester polymer is considerably 20 different from conventional unsaturated polyesters in that the amount of ethylenic unsaturation in the polyester can be lower than normal and the number average molecular weight can be lower than conventional polyesters. The amount of unsaturation is controlled by limiting the relative percent of unsaturated dicarboxylic acid to between 5 and 20 weight percent of total polyester. The 25 molecular weight of the polyester can be controlled by the ratio of total moles of glycol to total moles of dicarboxylic acid.

A further characteristic of the unsaturated polyester is that it must be essentially compatible with aliphatic acrylic or vinyl monomer in contrast with conventional polyesters being primarily compatible with aromatic styrene. Since 30 considerable amounts of vinyl and/or acrylic monomers are copolymerised with

the unsaturated polyester in accordance with this invention, the unsaturated polyester must contain polymeric units capable of solubility in the monomer mixture. Hence, less polar monomer components such as dimer acid, sebacic acid, or cyclohexane dicarboxylic acid should be added to the unsaturated polyester
5 formulation to avoid forming an undesirable sludge when mixed with the ethylenic monomers.

Hydroxyl functional polyesters can be prepared by esterification of the dicarboxylic acids with the dihydroxy or glycol compounds. The unsaturated polyester component can be synthesised by bulk polymerisation, where the raw
10 materials are charged in bulk and esterified at temperatures typically between 170°C and 240°C, although moderately higher or lower temperatures can be utilised satisfactorily. An esterification catalyst can be used, typically an organic tin compound at less than 1% levels based on weight of the charge.

The unsaturated polyester prepolymer can be dissolved in acrylic and/or vinyl
15 monomer to reduce the resin viscosity and render the polyester more easily dispersible in water. Lower molecular weight and lower viscosity unsaturated polyesters can be dispersed directly into water whereupon the ethylenic monomers can be added to the aqueous dispersion of polyester. The unsaturated polyester can be dispersed into water in the presence of a suitable dispersant, such as preferred
20 water dispersed epoxy-acrylic graft copolymer having carboxyl groups neutralised with amine or ammonia.

Ethylenic monomers suitable for aqueous polymerisation with the unsaturated polyester comprise monomers containing carbon-to-carbon, ethylenic unsaturation and include vinyl monomers, acrylic monomers, allylic monomers,
25 acrylamide monomers, and mono- and dicarboxylic unsaturated acids. Vinyl esters include vinyl acetate, vinyl propionate, vinyl butyrates, vinyl benzoates, vinyl isopropyl acetates and similar vinyl esters. Vinyl halides include vinyl chloride, vinyl fluoride, and vinylidene chloride. Vinyl aromatic hydrocarbons include styrene, methyl styrenes and similar lower alkyl styrenes, chlorostyrene,

vinyl toluene, vinyl naphthalene, divinyl benzoate, and cyclohexene. Vinyl aliphatic hydrocarbon monomers include alpha olefins such as ethylene, propylene, isobutylene, and cyclohexene as well as conjugated dienes such as 1,3 butadiene, methyl-2 butadiene, 1,3-piperylene, 2,3-dimethyl butadiene, isoprene, 5 cyclopentadiene, and dicyclopentadiene. Vinyl alkyl ethers include methyl vinyl ether, isopropyl vinyl ether, n-butyl vinyl ether, and isobutyl vinyl ether. Acrylic monomers include monomers such as lower alkyl esters of acrylic or methacrylic acid having an alkyl ester portion containing between 1 to 12 carbon atoms as well as aromatic derivatives of acrylic and methacrylic acid. Useful 10 acrylic monomer include, for example, acrylic and methacrylic acid, methyl acrylate and methacrylate, ethyl acrylate and methacrylate, butyl acrylate and methacrylate, propyl acrylate and methacrylate, 2-ethyl hexyl acrylate and methacrylate, cyclohexyl acrylate and methacrylate, decyl acrylate and methacrylate, isodecylacrylate and methacrylate, benzyl acrylate and 15 methacrylate, and various reaction products such as butyl, phenyl and cresyl glycidyl ethers reacted with acrylic and methacrylic acids, hydroxyl alkyl acrylates and methacrylates such as hydroxyethyl and hydroxy propyl acrylates and methacrylates, as well as amino acrylates and methacrylates. Carboxylic acid functional monomers can be included, if desired such as acrylic and methacrylic 20 acids. Ethylenic monomer mixtures of acrylic and/or methacrylic esters with styrene are preferred. Styrene copolymerises very efficiently with the double bond unsaturation in the polyester. On a weight basis of total ethylenic monomers, the ethylenic monomers preferably comprise between 20% and 100% styrene monomers, preferably between 30% and 70% styrene, with the balance being 25 other ethylenic monomers. At least 20% by weight should preferably be styrene monomer to assure copolymerisation and covalent linking to the unsaturated polyester.

The number average molecular weight of the emulsion polyester copolymer ordinarily is well above 50,000.

In accordance with the process of this invention, the unsaturated polyester is dispersed into water and copolymerised in the presence of a polymeric stabiliser. Preferred polymeric stabilisers comprise an epoxy-acrylic graft copolymer of the polymeric type taught in US 4 212 781. In this regard, epoxy resin is reacted with ethylenic monomer in the presence of at least 3% by weight benzoyl peroxide based on monomer weight, or free radical initiating equivalent peroxide, at a temperature preferably between about 80°C to 120°C to produce an epoxy-acrylic graft copolymer. In practice, the epoxy-acrylic graft copolymer is prepared in solvent and then subsequently dispersed into water using a fugitive base such as primary, secondary, and tertiary alkyl, alkanol, aromatic amines, or alkanolalkyl mixed amines such as mono-ethanol amine, dimethyl ethanol amine, diethanol amine, triethyl amine, dimethyl aniline, ammonium hydroxide, and the like.

The epoxy resin useful in preparing the epoxy-acrylic graft copolymer dispersant can be either aliphatic or aromatic, although the aromatic epoxy resins are preferred. The most preferred epoxy resins are polyglycidyl ethers of bisphenol-A, especially those having 1,2-epoxy equivalency between about 1.3 to about 2. The molecular weight should be from about 350 to about 20,000 and preferably from about 2,000 to about 10,000. Mixtures of monoepoxides and diepoxides are desirable, which maximises compatibility. Epoxy resins useful in the epoxy-acrylic graft copolymer are predominantly linear chain molecules comprising the coreaction product of polynuclear dihydroxy phenols or bisphenols with halohydrins to produce epoxy resins containing at least one and preferably two epoxy groups per molecule. The most common bisphenols are bisphenol-A, bisphenol-F, bisphenol-S, and 4,4'-dihydroxy bisphenol, with the most preferred being bisphenol-A. Halohydrins include epichlorohydrin, dichlorohydrin, and 1,2-dichloro 3-hydroxypropane with the most preferred being epichlorohydrin. Preferred epoxy resins comprise the coreaction product of excess molar equivalents of epichlorohydrin and bisphenol-A to produce predominantly an epoxy group terminated linear molecular chain of repeating units of diglycidyl

ether of bisphenol-A containing between 2 and 25 repeating copolymerised units of diglycidyl ether of bisphenol-A. In practice, excess molar equivalents of epichlorohydrin are reacted with bisphenol-A to produce epoxy resins where up to two moles of epichlorohydrin coreact with one mole of bisphenol-A. Less than 5 complete reaction can produce difunctional epoxy resin along with monoepoxide chains terminated at the other end with a bisphenol-A unit. The most preferred linear epoxy resins are poly-glycidyl ethers of bisphenol-A having an epoxy equivalent weight between 2,000 and 10,000, and a number average molecular weight from about 4,000 to 20,000 as measured by gel permeation 10 chromatography (GPC).

The acrylic portion of the epoxy-acrylic graft copolymer comprises polymerised ethylenically unsaturated monomers which include carboxyl functional monomers such as acrylic acid, lower alkyl substituted acrylic acids such as methacrylic acid, and unsaturated dicarboxylic acids such as maleic or 15 fumaric, to provide carboxyl functionality for dispersing the epoxy-acrylic copolymer mixture into water. The preferred acrylic acid is methacrylic acid. The balance of the monomers preferably are non-functional under the contemplated conditions of polymerisation, although small amounts of other reactive monomers may be used such as hydroxy monomers illustrated by 2-hydroxy ethyl 20 methacrylate, amide monomers illustrated by acrylamide, or N-methylol monomers illustrated by N-methylol acrylamide. The remaining monomers are non-functional but copolymerisable ethylenic monomers illustrated by acrylate and methacrylate esters, such as ethyl acrylate, methyl methacrylate or isobutyl methacrylate, styrene, or vinyl toluene, vinyl acetate, vinyl chloride, vinylidene 25 chloride, acrylonitrile, and generally alkyl esters of an acrylic acid, generally the lower alkyl esters, that is, those esters in which the esterifying group contains from 1 to 4 carbon atoms, and particularly ethyl acrylate. Other useful monomers alkyl acrylate esters and methacrylate esters such as, for example propyl acrylate, isopropyl acrylate, butyl acrylate, isobutyl acrylate, tertiary butyl acrylate, pentyl 30 acrylate, decyl acrylate, lauryl acrylate, isobornyl acrylate, methyl methacrylate,

butyl methacrylate, isobutyl methacrylate, hexyl methacrylate, 2-ethyl hexyl methacrylate, octyl methacrylate, and nonyl methacrylate. Other useful monomers are those readily commercial available monomers having vinyl unsaturation and include styrenic monomers such as styrene, vinyl toluene, divinyl benzene, 5 isoprene and butadiene. The acrylic, methacrylic or similar ethylenic carboxyl monomer preferably comprises by weight between about 5% and 40% based on the weight of the acrylic grafted epoxy copolymer.

The preferred epoxy-acrylic graft copolymer mixture is prepared by in-situ non-aqueous polymerisation of the ethylenic monomers with epoxy resin. The 10 epoxy resin can be heated in a reactor wherein the polymerisable monomer can be added slowly over a period of at least two or three hours along with a solvent and a free radical initiator. Although the reaction may be conducted in the absence of a solvent, some solvent is desirable for the in-situ polymerisation of monomers in the presence of epoxy resin. Solvents such as xylene, benzene, ethyl benzene, 15 toluene, and the alkoxy alkanols are satisfactory. Alcohols such as methanol, ethanol, propanol, butanol, and the like, are suitable, with ethylene glycol monobutyl ether and butanol being preferred. Ethylene glycol monobutyl ether, ethylene glycol monohexyl ether, diethylene glycol monobutyl ether, and the like are most suitable. For subsequent dispersion into water, the solvents selected 20 should be water-soluble materials, such as butanol, propanol, ethylene glycol monoethyl ether, and the like, although small amounts of mineral spirits, hexane, and similar aliphatics may be used.

In accordance with the process of the invention, the epoxy-acrylic graft copolymer dispersant is first dispersed into water by either direct or reverse let 25 down. The preformed unsaturated polyester is then dispersed into the aqueous medium to form a water dispersion of graft copolymer dispersant and unsaturated polyester. The ethylenically unsaturated monomers can be added separately to the water dispersion over a period of time, but preferably are added with the unsaturated polyester to provide increased fluidity to the unsaturated polyester and 30 improve dispensability into water. The ethylenically unsaturated polyester and

improve dispensability into water. The ethylenically unsaturated monomers are copolymerised in the aqueous polymerisation medium assisted with polymerising initiators. Initiators can include for example, typical free radical and redox types such as hydrogen peroxide, t-butyl hydroperoxide, di-t-butyl peracetate, 5 azobisisobutyronitrile, ammonium persulfate, sodium persulfate, potassium persulfate, sodium perphosphate, potassium perphosphate, isopropyl peroxy carbonate, and redox initiators such as sodium persulfate-sodium formaldehyde sulfoxylate, cumene hydroperoxide-sodium metabisulfite, potassium persulfate-sodium bisulfite, cumene hydroperoxide-iron (II) sulfate, 10 etc. The polymerisation initiators are usually added in amounts between about 0.1 to 2 weight percent based on the monomer additions, although higher levels can be utilised. The polymerisations process is continued until the ethylenically unsaturated monomers are completely copolymerised.

The resulting polymeric binder can be combined with other paint 15 ingredients for spray or roller application to metal substrates. For spraying, preferably the coating composition contains between about 10% and 40% by weight polymeric solids relative to 60% to 90% water including other volatiles such as minor amounts of solvents. Minor amounts of organic solvents can be utilised to facilitate spray or other application methods and such solvents 20 preferably include n-butanol and 2-butoxy-ethanol-1, with lesser amounts of aromatic naphtha, ethyl benzene, xylene, and toluene. Preferably n-butanol is used in combination with 2-butoxy-ethanol-1. For applications other than spraying, such as roller coating, the aqueous polymeric dispersions can contain between about 5% and 50% by weight of polymer solids. The coating composition of the 25 present invention can be pigmented and/or opacified with known pigments and opacifiers. For many uses, including food use, the preferred pigment is titanium dioxide. For interior of beer and beverage cans, clear coatings with minimal or no pigmentation are useful. Thus, spraying, rolling, dipping, and flow coating application methods can be used for both clear and pigmented films. After 30 application onto the metal substrate, the coating is cured thermally at temperatures

in the range from about 150°C to 220°C or higher for time sufficient to effect complete curing as well as volatising of any fugitive component therein.

For metal sheet substrates intended as beverage containers and particularly for carbonated beverages such as beer, the coating should be applied at a rate in the range from 0.5 to 15 milligrams of polymer coating per square inch of exposed metal surface. To attain the foregoing, the water-dispersible coating as applied can be as thick as 0.1 to 1 mil. Cured coating films exhibit excellent water resistance, good clarity and gloss, good flexibility, as well as good blush resistance to sterilisation and acidic foods and beverages.

- 10 For a better understanding of the present invention, the following examples are provided. In this application, all parts are by weight, all percentages are weight percentages, and temperatures are degrees Centigrade, unless otherwise expressly noted.

EXAMPLESExample 1 Preparation of Polyester Acrylic Copolymer

	<u>Material</u>	<u>Weight (kg)</u>
	<u>A: EPOXY-ACRYLIC GRAFT DISPERSANT</u>	
5	1. DER 331 Epoxy	100.10
	2. Diphenyl Propane (DPP)	55.60
	3. Butyl Oxitol	29.04
	4. Phosphonium Acetate	0.15
	5. Butyl Oxitol	0.51
10	6. Distillate	-2.17
	7. Deionised water (DI)	0.20
	8. Butyl Oxitol	5.61
	9. Butanol	38.53
	10. Methacrylic Acid	29.25
15	11. Styrene	37.51
	12. Ethyl Acrylate	0.75
	13. Benzoyl Peroxide (75%)	4.66
	14. Butyl Oxitol	12.29
	15. Butyl Oxitol	6.25
20	16. Dimethyl Ethanol Amine (DMEA)	18.58
	17. D.I. Water	371.61
	18. D.I. Water	13.38
	<u>B: DISPERSED POLYESTER ACRYLIC COPOLYMER</u>	
	19. Polyester Intermediate 1.1	14.78 (preformed below)
25	20. Styrene	28.27
	21. Butyl Acrylate	40.37
	22. t-Butyl Peroctoate	1.61
	23. Hexyl Glycol	0.34
	24. Butanol	5.17

25. t-Butyl Peroctoate	1.16
26. Hexyl Glycol	0.34
27. Butanol	5.17
28. Cymel 370 (Melamine)	31.63
5 29. Amine blocked dodecyl benzene sulfonic acid	5.45
30. D.I. Water	<u>143.19</u>
	1000.00

Procedure:

SET FOR VACUUM DISTILLATION; Charge components (1) + (2) + (3), and
10 heat to 50°C. Add components (4) + (5), and apply vacuum (better than 75mb).
Heat to Distillation, and remove at least stated quantity of Distillate (6).
Ordinarily vacuum is reduced to a level such that all the distillate is remove
without exceeding 120°C. Break vacuum with Nitrogen and replace excess
distillate with Butyl Oxitol (8).

15 SET FOR DIRECT REFLUX; Heat to 175-180°C slowly. Hold at 175-180°C and
sample for Cone & Plate @ 200°C of 50-60 poise. When at viscosity take final
sample, then add deionised water (7) and reheat to 175-180°C. Hold for 30
minutes, then cool and thin with Butyl Oxitol (8) and Butanol (9). Cool to
115-118°C, then add items 10 to 14 (PREMIXED) to reactants (1-9) over 2.5
20 hours. Rinse in with Butyl Oxitol (15) and hold for a further 30 minutes at
115-118°C.

To a separate vessel, charge DMEA (16) and DI water (17), and heat to 90-93°C.
These items should be held for 30 minutes at this temperature, and then mixed
with reactants (1-15) by adding the reactants slowly to preheated mixture (16 +
25 17) and with good stirring in order to ensure a good emulsion is formed. Some
minimal loss of reactants (1-15) can be expected due to the transfer between
vessels. Thin resulting mixture to approximately 31.5% (200°C/10min/1g) with DI
water (18). The resulting water dispersed resin is an epoxy-acrylic graft

copolymer dispersant used in the formation of the emulsion polyester acrylic copolymer as follows.

Reheat reactants (1-18) to 90-93°C and add materials (19), (20) and (21), and hold at 90-93°C for 45 minutes. Premix components (22), (23) and (24) and then add to 5 reactants (1-21), and hold for a further 3 hours @ 90-93°C. Premix components (25), (26) and (27) and then add to reactants (1-24), and hold for a further 1.5 hours @ 90-93°C. Cool reactants (1-27) to less than 40°C and then check NVM 35-37% (200°C/10min/1g). Add components (28), (29) and (30) and then thin to 45-55 seconds BSB4 @ 25°C with Nacure 29. The NVM should be 31-33% 10 (200°C/10min/1g).

C: PREPARATION OF POLYESTER INTERMEDIATE 1.1 USED AS COMPONENT (19) IN EXAMPLE 1

	<u>Item</u>	<u>Material</u>	<u>Weight</u>
	1.	Diethylene Glycol	228.61
15	2.	Isophthalic Acid	292.89
	3.	Butyl Stannoic Acid	0.86
	4.	Diethylene Glycol	168.11
	5.	Maleic Anhydride	172.40
	6.	Xylol	19.59
20	7.	Cyclohexane	<u>117.54</u>
			1000.00

Procedure:

Set reactor for Fractional Distillation and then add components (1), (2) and (3) to the reactor. Heat to Distillation and continue heating removing distillate (keep 25 column head temperature below 105°C) until a clear sample is obtained. Reaction temperature should not exceed 220°C. Cool to 180°C and add component (4), heat to 165°C, then add component (5), followed by reheating to 220°C removing distillate (keep column head temperature below 105°C). When column head temperature drops below 90°C change from a fractionating column to a plain

column. Sample reactants for Acid Value of less than 40 mgKOH/g and change to reflux and maintain a reflux at 220°C. Sample for Acid Value of 15-18 mgKOH/g. Cool and thin with component (7).

Example 2 : Preparation of Polyester-Acrylic Copolymer

5	<u>Material</u>	<u>Weight (kg)</u>
<u>A: PREPARATION OF EPOXY-ACRYLIC GRAFT DISPERSANT</u>		
	1. DER 331 (Epoxy)	105.66
	2. D.P.P.	58.63
	3. Butyl Oxitol	30.62
10	4. Phosphonium Acetate	0.16
	5. Butyl Oxitol	0.53
	6. Distillate	-2.29
	7. D.I. Water	0.44
	8. Butyl Oxitol	5.19
15	9. Butanol	40.62
	10. Methacrylic Acid	30.85
	11. Styrene	39.55
	12. Ethyl Acrylate	0.79
	13. Benzoyl Peroxide (75% damped)	4.91
20	14. Butyl Oxitol	12.96
	15. Butyl Oxitol	6.59
	16. D.M.E.A.	19.59
	17. D.I. Water	391.84
	18. D.I. Water	14.11

25 B: PREPARATION OF POLYESTER-ACRYLIC COPOLYMER

19. Polyester Intermediate 2.1	10.88 (preformed below)
20. Styrene	20.48
21. Butyl Acrylate	29.26

	22. Triganox 21	1.17
	23. Hexyl Glycol	0.33
	24. Butanol	5.49
	25. t-Butyl Peroctoate	1.17
5	26. Hexyl Glycol	0.33
	27. Butanol	5.49
	28. Cymel 370	30.56
	29. Amine blocked dodecyl benzene sulfonic acid	5.24
10	30. D.I. Water	<u>128.23</u>
		1000.00

The processing procedure for the above components was the same as Example 1.

C: PREPARATION OF POLYESTER INTERMEDIATE 2.1 FOR USE AS
COMPONENT (19) IN EXAMPLE 2

15	<u>Item</u>	<u>Material</u>	<u>Weight</u>
	1.	Diethylene Glycol	295.47
	2.	Isophthalic Acid	389.08
	3.	Butyl Stannoic Acid	0.86
	4.	Diethylene Glycol	85.57
20	5.	Maleic Anhydride	85.57
	6.	Xylol	10.67
	7.	Cyclohexane	<u>132.78</u>
			1000.00

Procedure:

25 Set for Fractional Distillation. Charge components (1), (2) and (3), and heat to Distillation. Continue heating removing distillate (keep column head temperature below 105°C) until a clear sample is obtained. The reaction temperature should not exceed 220°C. Cool to 180°C and add Diethylene glycol (4). Upheat to 165°C

and then add maleic anhydride (5), and reheat to 220°C removing distillate (keep column head temperature below 105°C). When column head temperature drops below 90°C change from a fractionating column to a plain column. Sample reactants for Acid Value of less than 40 mgKOH/g, change to flux set up and add 5 xylol (6) to maintain a reflux at 220°C. Sample for Acid Value of 15-18 mgKOH/g. Cool and thin with Cyclohexanone (7).

Example A

Reference material epoxy polyester with N-i-BMA in aqueous stage polymerisation

10	<u>Material</u>	<u>Weight</u>
	1. DER 331 Epoxy resin	109.14
	2. D.P.P.	60.62
	3. Butyl Oxitol	31.66
	4. Phosphonium Acetate	0.16
15	5. Butyl Oxitol	0.55
	6. Distillate	-2.36
	7. D.I. Water	0.46
	8. Butyl Oxitol	6.12
	9. Butanol	40.01
20	10. Methacrylic Acid	31.90
	11. Styrene	40.89
	12. Ethyl Acrylate	0.81
	13. Benzoyl Peroxide (75% damped)	5.07
	14. Butyl Oxitol	13.39
25	15. Butyl Oxitol	6.81
	16. D.M.A.E.	22.15
	17. D.I. Water	405.15
	18. D.I. Water	14.58
	19. N-iso butoxy methyl acrylamide	12.05

	20. Ethyl Acrylate	48.20
	21. t-Butyl Peroctoate	1.21
	22. Hexyl Cellosolve	0.34
	23. Butanol	5.62
5	24. t-Butyl Peroctoate	1.21
	25. Hexyl Cellosolve	0.34
	26. Butanol	5.65
	27. Cymel 370	31.34
	28. Nacure 5925	1.39
10	29. D.I. Water	<u>99.51</u>
		1000.00

The Procedure was as in Example 1, except: Reheat items (1) to (18) to 90-93°C and add 19 to 20 then hold at 90-93°C for 45 minutes. Add (21), (22) and (23) Premixed, and hold for a further 3 hours @ 90-93°C. Add (24), (25) and (26) 15 Premixed, and hold for a further 1.5 hours @ 90-93°C. Cool to less than 40°C Check NVM 35-37% (200°C/10min/1g). Add components (27), (28) and (29). Thin reactants to 45-55 seconds Bss4 @ 25°C with DI water (29). NVM should be 31-33% (200°C/10min/1g).

The following Table 1 reports physical properties of coated panels with films 20 formed from the foregoing Examples 1, 2 and A.

Table 1

	Test	Example 1	Example 2	Reference Example A
	MEK cure	>100	>100	>100
	Wedge bend flexibility	89	90	80
25	Sterilisation blush	2	1	1
	Sterilisation adhesion	1	1	1
	Enamel rater 206 shell	0.85	1.12	1.42
	Post-sterilisation ER	3.01	1.15	3.56

Example 3 : Preparation of Polyester Acrylic Copolymer

	<u>Material</u>	<u>Weight (kg.)</u>
<u>A: EPOXY-ACRYLIC GRAFT DISPERSANT</u>		
	1. DER 331	117.08
5	2. D.P.P.	64.24
	3. Butyl Oxitol	22.85
	4. Phosphonium Acetate	0.18
	5. Butyl Oxitol	0.66
	6. Distillate	-3.32
10	7. D.I. Water	0.13
	8. Butyl Oxitol	11.63
	9. Butyl Oxitol	48.79
	10. Methacrylic Acid	34.63
	11. Styrene	42.00
15	12. Ethyl Acrylate	0.84
	13. Benzoyl Peroxide (75% damped)	5.34
	14. Butyl Dioxitol	17.01
	15. Butyl Oxitol	4.25
	16. D.M.E.A.	18.43
20	17. D.I. Water	426.63
	18. D.I. Water	22.83
<u>B: DISPERSED POLYESTER ACRYLIC COPOLYMER</u>		
	19. Polyester Intermediate 3.1	14.03 (preformed below)
	20. Styrene	17.78
25	21. Butyl Acrylate	31.80
	22. t-Butyl Preoctoate	1.27
	23. Butyl Dioxitol	5.17
	24. Butanol	1.15
	25. t-Butyl Preoctoate	1.27

6. Butyl Dioxitol	6.31
27. Cymel 370	32.31
28. Amine blocked dodecyl benzene sulfonic acid	1.43
9. D.I. Water	<u>53.28</u>
5	1000.00

Procedure:

SET FOR VACUUM DISTILLATION; Charge components (1), (2) and (3) and heat to 50°C. Add components (4) and (5) and apply vacuum (better than 75mb). Heat to Distillation, and remove at least stated quantity of Distillate. Break
 10 vacuum with Nitrogen and replace excess distillate with Butyl Oxitol while distillate is removed without exceeding 120°C).

SET FOR DIRECT REFLUX; Heat reactants to 175-180°C slowly and hold at 175-180°C for viscosity sample for Cone & Plate @ 200°C of 50-60 poise. When at viscosity take final sample, then components (7) and (8), and reheat to
 15 175-180°C. Hold for 30 minutes, then cool and thin with component (9). Cool to 115-118°C, then add items (10) to (14) (PREMIXED) to reactants (1) to (9) over 2.5 hours. Rinse in with Butyl Oxitol (15) and hold for a further 30 minutes at 115-118°C. Add DMEA (16) and hold at 100-105°C for 30 minutes. Add DI water (17) slowly to ensure a good emulsion, then thin to approximately 31.5%
 20 (200°C.10min/1g) with DI water (18). Premix components (19), (20) and (21) and add to reheated reactants (1) to (18) to 90-93°C and hold at 90-93°C for 45 minutes. Add components (22), (23) and (24) (Premixed), and hold for a further 3 hours @ 90-93°C. Add components (25) and (26) (Premixed), and hold for a further 1.5 hours @ 90-93°C. Cool reactants to less than 40°C Check NVM
 25 34-35% (200°C.10min/1g). Add components (27) and (28), and then thin 45-55 seconds BSB4 @ 25°C with DI water (29). NVM should be 33-35% (200°C/10min/1g).

C: PREPARATION OF POLYESTER INTERMEDIATE 3.1 FOR USE AS
COMPONENT (19) IN EXAMPLE 3

	<u>Item</u>	<u>Material</u>	<u>Weight</u>
	1.	Diethylene Glycol	673.4
5	2.	Isophthalic Acid	664.9
	3.	Butyl Stannoic Acid	1.95
	4.	Sebacic Acid	269.7
	5.	Diethylene Glycol	195.0
	6.	Maleic Anhydride	195.0
10	7.	1,4-Benzoquinone, 98%	0.33
	8.	Styrene	<u>740.5</u>
			2740.78

Procedure:

Set for Fractional Distillation. Charge components (1), (2) and (3), then heat to
15 Distillation. Continue heating removing distillate (keep column head temperature
below 105°C) until a clear sample is obtained without reactants exceeding 220°C.
Cool to 180°C and add Sebacic Acid (4). Reheat to 220°C removing distillate
(keep column head temperature below 105°C). Sample reactants for Acid Value of
less than 20mgKOH/g. Cool to 180°C and add Diethylene Glycol (5), then add
20 Maleic Anhydride (6), when the temperature is below 165°C. Reheat to 220°C and
hold @ 220°C for 1 hour (removing any distillate produced). Change over to Dean
and Stark reflux, and add Xylol to maintain a good reflux. Sample reactants for
Acid Value of 15-18 mgKOH/g. Cool to 100°C and add the polyester to premixed
components (7) and (8), but do not allow the resulting reaction mixture
25 temperature to exceed 50°C.

PHYSICAL CHARACTERISTICS:

Acid Value: 15-18 mgKOH/g.

Solid Content: 67-68% (200°C/10minutes/1g)

Example 4

	<u>Item</u>	<u>Material</u>	<u>Weight</u>
<u>A: PREPARATION OF AN ALTERNATIVE POLYESTER ACRYLIC COMPOSITION USING POLYESTER INTERMEDIATE 4.1 AS FOLLOWS</u>			
5	1.	Diethylene Glycol	673.4
	2.	Isophthalic Acid	531.9
	3.	Butyl Stannoic Acid	1.95
	4.	1,4-Cyclohexanedicarboxylic Acid	363.1
	5.	Diethylene Glycol	195.0
10	6.	Maleic Anhydride	195.0
	7.	1,4-Benzoquinone, 98%	0.33
	8.	Styrene	<u>720.5</u>
			2681.18

Processing Procedure : same as in Example 3.1

15 PHYSICAL CHARACTERISTICS OF RESULTING DISPERSANT RESIN:

Acid Value: 15-18mgKOH/g; Solid Content: 67-68% (200°C/10minutes/1g)

Upon adding preformed polyester 4.1 to the dispersant (1 to 18), components (19), (20) and (21) can be pre-mixed for easier processing. Polyester 4.1 was substituted into the composition of Example 3 to give the following film test results in Table 2.

Table 2

Test	Polyester 4.1 in Example 3	Example 3
MEK cure	>100	>100
Wedge bend flexibility	90%	85%
25 Sterilisation blush	1/2	1/2
Sterilisation adhesion	1	1
Enamel rater 206 shell	0.60	1.57
Post - sterilisation ER	1.48	1.73

Examples 5 and 6

Components were reacted in the procedure indicated in a manner similar to Examples 1 to 4.

		Example 4	Example 5
A	DER331 Epoxy	49.67	49.67
B	2-Phenyl Imidazole	0.0037	0.0037
B	Solvesso 100	0.15	0.15
C	Bisphenol A	27.34	27.34
C	Solvesso 100	4.05	4.05
D	Hexyl Cellosolve	3.019	3.19
D	Butyl Cellosolve	16.48	16.48
D	n-Butanol	20.42	20.42
E	Methacrylic Acid	14.24	14.24
E	Styrene	8.58	8.58
E	Ethyl Acrylate	0.18	0.18
E	BPO-78%	2.24	2.24
E	Hexyl Cellosolve	4.95	4.95
F	Dimethyl ethanol amine	9.09	9.09
F	De-ionized Water	9.09	9.09
G	De-ionized Water	486.97	486.97
H	Styrene	8.33	15
H	Butyl Acrylate	15	15
H	Polyester example 4.1	6.66	
I	t-Butyl PerOctoate	0.6	0.6
J	Styrene	36.67	36.67
K	t-Butyl PerOctoate	0.73	0.73
L	Butanol	7.94	7.94
L	De-ionized Water	171.39	171.39
L	Dimethyl ethanol amine	4.78	4.78

- 1) Heat A in a flask to 70°C and add B.
- 5 2) Continue to heat to 90°C and then add C.
- 3) Heat to 195°C and hold until an EEW of 2700-3500 is achieved.

- 4) Add D and cool to 118°C.
- 5) Pre-mix E and add to the flask over 2 hours.
- 6) Hold 118°C after E feed is completed.
- 7) Cool to 95°C and add F.
- 5 8) Maintain 95°C for 45 minutes.
- 9) Add G over 60-90 minutes to emulsify; maintain 90°C minimum.
- 10) Add H and mix for 45 minutes.
- 11) Add I and hold for 3 hours.
- 12) Add J and mix for 45 minutes.
- 10 13) Add K and hold for 3 hours.
- 14) Cool to 30°C and add L. Mix well.
- 15) Filter.

Resin film samples from Examples 4 and 5 were tested and the results are shown in Table 3 as follows.

15 **Table 3**

	Example 4	Example 5 (no polyester)
Non-volatile content	18.9%	19.0%
Viscosity (sec #4 Ford cup)	18	18
Pine Oil (mg adsorbed)	5.5	3.7
Limonene (mg adsorbed)	1.9	3.8 (heavy blush)

Viscosity and NV for 12040-16A and 12040-16B were 18"/19% and 18"/18.9%, respectively.

Two odour absorption tests, Pine Oil and Limonene, were done as follows. Formulations were drawn down on Al Foil strips and baked for 30" at 360°F; then
20 coated on the opposite side and baked for 60" at 360°F. 4in x 5in coupons were made from the coated strips and hole punched; then weighed. Typically six coupons were hung from a rod through the punched holes above a solution of 1/2g per gallon of either Pine Oil or Limonene for 3 days at 100°F in an oven. When

the exposure was complete the coupons were reweighed and the difference reported in milligrams. Any blushing or haziness was also recorded.

The foregoing detailed description and illustrative examples illustrate the merits of the invention but are not intended to limit the scope of the invention, except by
5 the appended claims.

CLAIMS

1. An aqueous dispersed, protective coating composition containing an emulsion copolymer polymeric binder substantially free of volatile organic compounds, the polymeric binder comprising by weight:
- 5 (a) between 0.1% and 40% of a preformed, low molecular weight unsaturated polyester having a weight average molecular weight between 1000 and 3000, the unsaturated polyester synthesised by esterifying excess molar equivalents of polyol with lesser molar equivalents of dicarboxylic acid, at molar percents between,
- 10 (i) 0.5 and 50 mol percent polyol consisting of glycol,
- (ii) 10 and 35 mol percent aliphatic dicarboxylic acid,
- (iii) 5 and 35 mol percent aromatic dicarboxylic acid,
- (iv) 5 and 25 mol percent unsaturated dicarboxylic acid,
- (v) 0 and 3 mol percent polyol having three or more hydroxyl groups;
- 15 (b) at least 20% of in-situ, emulsion copolymerised ethylenic monomers, where the ethylenic monomers comprise at least 20% styrene based on the weight of the ethylenic monomers copolymerised; and
- (c) between 20% and 80% carboxyl functional epoxy-acrylic graft copolymer dispersant, the copolymer dispersant having an Acid No. greater than 30, the
- 20 copolymer dispersant being by weight 5% to 80% epoxy resin and 20% and 95% copolymerised ethylenically unsaturated monomer including carboxylic acid monomer, the graft copolymer dispersant produced by in-situ, non-aqueous polymerisation of the ethylenically unsaturated monomers in the presence of the epoxy resin and at least 3% peroxide initiator based on the weight of said
- 25 monomers copolymerised, to produce the carboxyl functional, epoxy-acrylic graft copolymer dispersant;

where components (a), (b) and (c) equal 100%, and the polymeric binder is produced by dispersing the copolymer dispersant (c) into water, and the unsaturated polyester (a) and the monomers (b) being dispersed into water with the copolymer dispersant (c), and the monomers (b) emulsion copolymerised in the presence of the unsaturated polyester (a) to coreact with the unsaturated polyester to form the aqueous emulsion copolymer polymeric binder.

2. The coating composition of Claim 1 wherein component (b) comprises 20% and 80% by weight of the polymeric binder.
3. The coating composition of Claim 1, wherein the ethylenic monomers in component (b) comprise between 20% and 100% styrene based on the weight of said monomers copolymerised.
4. The coating composition in Claim 1, wherein the ethylenic monomers in component (b) comprise between 30% and 70% styrene based on the weight of said monomers copolymerised.
5. The coating composition of Claim 1, wherein the molar equivalent excess of polyol over dicarboxylic acid in component (a) is between 2% and 25%.
6. The coating composition of Claim 1, in component (a), between 20 and 50 molar percent of the dicarboxylic acid components comprise unsaturated dicarboxylic acid.
7. The coating composition of Claim 1, wherein the relative weight percents of component (a) and component (b) comprise 0.5% to 50% of component (a) and 50% to 99.5% of component (b).
8. The coating composition of Claim 1, wherein the weight average molecular weight of component (a) is between 1500 and 2500.
9. The coating composition of Claim 1, wherein polymeric binder is produced by component (c) being dispersed into water to form a water dispersion, and then component (a) and component (b) being premixed prior to dispersing into the water dispersion of component (c).

10. The coating composition of Claim 1, wherein the polymeric binder is produced by dispersing component (c) into water to form a water dispersion of component (c), where component (a) is then dispersed into the water dispersion of component (c), followed by in-situ copolymerisation of component (b).

5 11. An aqueous dispersed, protective coating composition containing an emulsion copolymer polymeric binder substantially free of volatile organic compounds, the polymeric binder comprising by weight:

(a) between 0.1% and 40% of a preformed, low molecular weight unsaturated polyester having a weight average molecular weight between 1000
10 and 3000, the unsaturated polyester synthesised by esterifying molar equivalents of polyol with molar equivalents of dicarboxylic acid, at molar percents between,

(i) 0.5 and 50 mol percent polyol consisting of glycol,

(ii) 10 and 35 mol percent aliphatic dicarboxylic acid,

(iii) 5 and 35 mol percent aromatic dicarboxylic acid,

15 (iv) 5 and 25 mol percent unsaturated dicarboxylic acid,

(v) 0 and 3 mol percent polyol having three or more hydroxyl groups;

(b) at least 20% of in-situ, emulsion copolymerised ethylenic monomers, where the ethylenic monomers comprise at least 20% styrene based on the weight of the ethylenic monomers copolymerised; and

20 (c) between 20% and 80% of a water dispersed carboxyl functional copolymer dispersant;

where components (a), (b) and (c) equal 100%, and said polymeric binder is produced by dispersing the water dispersed copolymer dispersant and the unsaturated polyester into an aqueous polymerisation medium, and emulsion
25 copolymerising the ethylenic monomers in the presence of the unsaturated polyester to coreact the ethylenic monomers with the unsaturated polyester to form the aqueous emulsion copolymer polymeric binder.

12. A process of producing an aqueous dispersed, protective coating composition containing an emulsion copolymer polymeric binder substantially free of volatile organic compounds, the process comprising:

(a) preforming a carboxyl functional epoxy-acrylic graft copolymer dispersant
5 having an Acid No. greater than 30 and comprising by weight between 5% and 80% epoxy resin and between 20% and 95% copolymerised ethylenically unsaturated monomer including carboxyl monomer, the graft copolymer produced by in-situ, non-aqueous polymerisation of said monomers in the presence of the epoxy resin and at least 3% peroxide initiator based on the weight of said
10 monomers copolymerised to produce the graft copolymer dispersant, and then dispersing the graft copolymer into water;

(b) preforming a low molecular weight unsaturated polyester having a weight average molecular weight between 1000 and 3000, the unsaturated polyester synthesised by esterifying excess molar equivalents of polyol with lesser molar
15 equivalents of dicarboxylic acid, the molar equivalents comprising,

(i) 0.5 and 50 mol percent polyol consisting of glycol,

(ii) 10 and 35 mol percent aliphatic dicarboxylic acid,

(iii) 5 and 35 mol percent aromatic dicarboxylic acid,

(iv) 5 and 25 mol percent unsaturated dicarboxylic acid,

20 (v) 0 and 3 mol percent polyol having three or more hydroxyl groups

(c) dispersing the preformed unsaturated polyester of step (b) into the water containing the dispersed graft copolymer of step (a) along with emulsion ethylenic monomers, the emulsion ethylenic monomers comprising at least 20% styrene based on the weight of the emulsion ethylenic monomers copolymerised; and

25 (d) emulsion copolymerising the emulsion ethylenic monomers in the presence of the water dispersed unsaturated polyester to addition copolymerise and crosslink the emulsion ethylenic monomers with the water dispersed unsaturated polyester

to form the aqueous emulsion copolymer polymeric binder, the polymeric binder comprising by weight between 0.1% and 40% crosslinked preformed unsaturated polyester, between 20% and 80% emulsion copolymerised ethylenic monomers, and between 20% and 80% graft copolymer dispersant.

5 13. The process of Claim 12, wherein the preformed unsaturated polyester in step (b) and emulsion ethylenic monomers are premixed prior to the step (c) of dispersing into water.

14. The process of Claim 12, wherein the preformed unsaturated polyester of step (b) is dispersed into water, and then the emulsion ethylenic monomer are added to
10 the water and emulsion copolymerised in the presence of the unsaturated polyester.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 99/02279

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C09D151/00 C08F283/01 C08F290/14

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C09D C08F C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4 683 273 A (BODE DANIEL) 28 July 1987 (1987-07-28) cited in the application * column 1, line 54 - column 4, line 65 ; column 5, line 67-68 ; column 5, line 7-62* column 6, line 59-66 ---	1-14
Y	WO 97 30097 A (PPG INDUSTRIES INC) 21 August 1997 (1997-08-21) * page 6, line 1 - page 10, line 24 ; page 15, line 8-9 ; page 17, line 16 - page 18, line 2 * page 22, line 19-21 --- -/--	1-14

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"3" document member of the same patent family

Date of the actual completion of the international search

7 July 1999

Date of mailing of the international search report

27/07/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Hammond, A

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 99/02279

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5 464 885 A (CRAUN GARY P) 7 November 1995 (1995-11-07) cited in the application the whole document ---	1-14
Y	EP 0 640 654 A (BASF AG) 1 March 1995 (1995-03-01) * claims 1-3 ; page 4, line 29-51 ; page 4, line 19-24 ; page 2, line 28 - page 3, line 21 * page 5, line 9 ---	1-14
Y	US 5 532 297 A (WOO JAMES T K ET AL) 2 July 1996 (1996-07-02) cited in the application the whole document ---	1-14
Y	US 5 648 410 A (HILLE HANS DIETER ET AL) 15 July 1997 (1997-07-15) * column 2, line 25 - column 4, line 59 * column 5, line 29-39; claims 1-33 ---	1-14
A	EP 0 629 643 A (GLIDDEN COMPANY FORMERLY KNOWN) 21 December 1994 (1994-12-21) page 3, line 9-22 ---	1-14
A	EP 0 622 417 A (BASF AG) 2 November 1994 (1994-11-02) * claims 1,3 ; page 4, line 33 - page 5, line 3 ; page 4, line 19-24 * page 2, line 28-36 ---	1-14
A	US 4 212 781 A (EVANS JAMES M ET AL) 15 July 1980 (1980-07-15) cited in the application claims 1-75 -----	1-14

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 99/02279

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4683273	A	28-07-1987	NONE	
WO 9730097	A	21-08-1997	US 5830928 A	03-11-1998
US 5464885	A	07-11-1995	NONE	
EP 0640654	A	01-03-1995	DE 4325886 A	09-02-1995
US 5532297	A	02-07-1996	NONE	
US 5648410	A	15-07-1997	DE 4242518 A	23-06-1994
			AT 155500 T	15-08-1997
			AU 5810394 A	04-07-1994
			CN 1090293 A	03-08-1994
			DE 59306944 D	21-08-1997
			WO 9413720 A	23-06-1994
			EP 0674672 A	04-10-1995
			ES 2107802 T	01-12-1997
EP 0629643	A	21-12-1994	US 5290828 A	01-03-1994
			AU 670502 B	18-07-1996
			AU 6458294 A	15-12-1994
			CA 2124235 A,C	12-12-1994
			DE 69406591 D	11-12-1997
			NZ 260401 A	26-01-1996
			SG 47870 A	17-04-1998
			ZA 9403835 A	08-03-1995
EP 0622417	A	02-11-1994	DE 4314306 A	02-02-1995
US 4212781	A	15-07-1980	AU 512156 B	25-09-1980
			AU 2504677 A	16-11-1978
			BE 854476 A	10-11-1977
			BR 7703049 A	08-02-1978
			DE 2721822 A	24-11-1977
			DK 204977 A	12-11-1977
			FI 771481 A	12-11-1977
			FR 2393021 A	29-12-1978
			GB 1585486 A	04-03-1981
			HK 48881 A	16-10-1981
			JP 1506613 C	13-07-1989
			JP 53001228 A	09-01-1978
			JP 63017869 B	15-04-1988
			NL 7705237 A,B,	15-11-1977
			NZ 184048 A	08-05-1980
			SE 444443 B	14-04-1986
			SE 7705300 A	12-11-1977